

TECHNICAL DATA SHEET

POLYPROPYLENE TATREN HT 3 06

Homopolymer for weaving tapes

TIPELIN / TIPOLEN / TIPPLEN / TATREN / BRALEN+

The joint product portfolio of MOL Petrochemicals and Slovnaft provides infinite opportunities

DESCRIPTION

TATREN HT 3 06 is a homopolymer of good processing stability and it can be processed at high throughput. Additive package of this grade provides low water carry over during production of tapes. **TATREN HT 3 06** is characterised by exceptionally high mechanical properties and high stiffness.

APPLICATIONS

TATREN HT 3 06 is intended for production of high tenacity weaving tapes and monofilaments. It is well suitable to produce PP fabrics for big-bags production, carpet backing, ropes and marine ropes, twines etc. This grade can be used also for extrusion, sheet extrusion and thermoforming, injection moulding and compounding.

TATREN HT 3 06 is suitable for food contact. The product complies with Food Contact Regulations. The grade is suitable for manufacturing of pharmaceutical packing-product.

PROPERTIES

	Test method	Unit	Typical value
MFR (230 °C/2.16 kg)	ISO 1133-1	g/10 min	3.0
Tensile stress at yield *	ISO 527-1,2	MPa	37
Tensile strain at yield *	ISO 527-1,2	%	8
Modulus of elasticity in tension *	ISO 527-1,2	MPa	1900
Flexural modulus *	ISO 178	MPa	1950
Izod impact strength (notched, 23 °C) *	ISO 180/A	kJ/m ²	6
HDT (0.45 MPa, flatwise) *	ISO 75-1,2	°C	107
Rockwell hardness *	ISO 2039-2	R scale	105

Typical properties, not to be used as specification.

* Typical properties measured on standard injection moulded test specimen according to ISO 294-1.

PROCESSING

TATREN HT 3 06 can be processed on standard extrusion machines. Recommended processing temperatures are 230 - 260 °C.

TECHNICAL DATA SHEET

POLYPROPYLENE TATREN HT 3 06

Homopolymer for weaving tapes

TIPELIN / TIPOLEN / TIPPLEN / TATREN / BRALEN+

The joint product portfolio of MOL Petrochemicals and Slovnaft provides infinite opportunities

2

STORAGE AND HANDLING

Pellets are packed in 25 kg PE-LD bags and transported on stretch or shrink-wrapped pallets at eligible load of polymer 1375 kg. Heat treated pallets are available as well. We use adhesive between the bags in order to avoid their slipping. Pay attention to this fact during the removing of the bags from the pallets. The preferred method is to lift the bag at first without rotation. Transportation in a road silo or rail silo is also available. For more detailed information please contact SLOVNAFT and MOL Petrochemicals sales representative.

Since polypropylene is a combustible substance, the fire safety rules applicable for combustible materials in warehouses and store rooms should be observed.

If polymer is stored in conditions of high humidity and fluctuating temperatures, then atmospheric moisture can condense inside the packing. If it happened, it is recommended the pellets to be dried before use. During the storage polypropylene should not be exposed to UV radiation and temperatures above 40°C. Producer does not take responsibility for any damages caused by adverse storage.

REACH STATEMENT

Polymers are exempt of REACH registration. However, their raw materials which mean monomers and relevant additives have been registered. SLOVNAFT, a.s. is committed to fully respect legislation and will only use REACH compliant raw materials. At this point in time PP TATREN does not contain any substances specifically identified as SVHC at levels greater than 0.1%.

SAFETY

See MSDS.

RECYCLING

Polypropylene resins are suitable for recycling using modern recycling methods. In-house production waste should be kept clean to facilitate direct recycling.

DISCLAIMER

©2018 MOL Group. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a web site. MOL Group does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "MOL", or "MOL Group" are used for convenience, and may include any one or more of MOL Group, or any affiliates they directly or indirectly control. MOL Group, the MOL Group logo, and all other product names used herein are trademarks of MOL Plc. or SLOVNAFT, a.s. unless indicated otherwise.

TECHNICAL DATA SHEET

POLYPROPYLENE TATREN HT 3 06

Homopolymer for weaving tapes

TIPELIN / TIPOLEN / TIPPLEN / TATREN / BRALEN+

The joint product portfolio of MOL Petrochemicals and Slovnaft provides infinite opportunities

MANUFACTURER

SLOVNAFT, a.s.

Vlčie hrdlo 1
824 12 Bratislava
Slovak Republic
E-mail: infopolymer@slovnaft.sk

TECHNICAL SERVICE

SLOVNAFT, a.s.

Vlčie hrdlo 1
824 12 Bratislava
Slovak Republic
Telephone:
+ 421 2 5859 7250
+ 421 2 5859 7257
E-mail: polymerservice@slovnaft.sk

SALES ORGANIZATION

GERMANY

Im Trutz Frankfurt 49,
D-60322 Frankfurt am Main, Germany
Telephone: +49 69 154 04 0
Fax: +49 69 154 04 41
E-mail: polymersales@molgermany.de

ITALY

Via Montefeltro, 4
20156 Milano, Italy
Telephone: +39 02 58 30 5523
Fax: +39 02 58 30 3492
E-mail: tvk.info@molgroupitaly.it

POLAND

Ul. Postępu 17D
02-676 Warszawa, Poland
Telephone: +48 22 545 70 70
Fax: +48 22 545 70 60
E-mail: petchem@slovnaft.pl

AUSTRIA

Walcherstrasse 11A, 7.Stock
A- 1020 Wien, Austria
Telephone: +43 1 211 20 1120
Fax: +43 1 211 20 1198
E-mail: JHauk@molaustria.at

FRANCE

Paris, France
Mobile Phone: + 33 7 89 86 10 64
Telephone: + 33 1 64 32 44 17
E-mail: iren.husson@molgroupitaly.it

ROMANIA

Str. Danielopolu 4-6
ET1 Sector 1 Cod 014 134
Bucuresti, Romania
Telephone:
+40 21 204 85 00
+40 21 204 85 02
Fax: +40 21 232 10 59
E-mail: petchem@molromania.ro

TECHNICAL DATA SHEET

POLYPROPYLENE TATREN HT 3 06

Homopolymer for weaving tapes

TIPELIN / TIPOLEN / TIPPLEN / TATREN / BRALEN+

The joint product portfolio of MOL Petrochemicals and Slovnaft provides infinite opportunities

4

HUNGARY

H-3581 Tiszaújváros,
P.O. Box: 20
Hungary
Telephone: +36 49 531 928
Fax: +36 1 8877 647
E-mail: polymersales@mol.hu

UKRAINE

04073 Kiev
Stepana Bandery ave., 23, 7th floor, of. 305,
Ukraine
Telephone:
+380 44 374 00 80
+380 67 463 58 69
Fax: +380 44 374 00 90
E-mail: JZavojko@mol-ukraine.com.ua

OTHER EUROPEAN COUNTRIES

Telephone:
+36 20 506 6572
+36 70 373 9209
Fax: + 36 1 8877 647
E-mail: polymersales@mol.hu

SLOVAKIA AND CZECH REPUBLIC

Vlčie hrdlo 1
824 12 Bratislava, Slovak Republic
Telephone:
+ 421 2 5859 7515
+ 421 2 5859 7622
+ 421 2 5859 7741
+ 421 2 5859 7231
E-mail: polymersales@slovnaft.sk

CROATIA, SLOVENIA, SERBIA, MONTENEGRO, BOSNIA AND HERZEGOVINA, FYR MACEDONIA, ALBANIA, KOSOVO

Zadarska 80
HR-10000 Zagreb, Croatia
Telephone: +385 1 6160 600
Fax: +385 1 6160 601
E-mail: polymersales@tifon.hr

April 2019