

Grade	2600F
Product	HDPE

General Information

Key Features

- High processability and high speed
- Suitable for the processing - at high spinning speed - of fibers and non-woven fabrics.

Applications

Bi-component fiber (PET/PE, PP/PE)

Item	Measuring Method	Unit	Value
Physical			
Melt Flow Index	ASTM D1238	g/10min	18.0
Density	ASTM D1505	g/cm ³	0.959
Mechanical			
Tensile Stress (Yield)	ASTM D638	kgf/cm ²	245
Tensile Strain (Break)	ASTM D638	%	≥300
Flexural Modulus	ASTM D790	kgf/cm ²	12,500
Impact			
Izod Impact Strength(notched) (23°C)	ASTM D256	kgf·cm/cm	4
Thermal			
VICAT Softening Temperature	ASTM D1525	°C	120
Additional Properties			

1. Physical Properties : these are not to be construed as specifications
2. ISO 9001, 14001, /TS 16949

* The last update date : 2021/10/01