

**Physical Properties** 

수정일자 2013. 05. 27

LOTTE CHEMICAL RESEARCH INSTITUTE 115 Gajeong-book St. Yusung, Dajeon TEL) 042-879-1261,1262

# Adpoly TU-100

### **Adhesive Resin**

#### **General Information**

## Description

TU-100 is LDPE based adhesive resin containing anhydride.

This grade shows a strong adhesion to PE, PA, EVOH, and it has polyolefin-like properties. In addition, its processability is excellent.

TU-100 is mainly intended for use as an adhesive resin in multi-layer bottle.

# Applications

Multi-layer bottle/sheet for food & cosmetic packaging

| Physical Properties <sup>1</sup>   |             |         |                     |      |     |
|------------------------------------|-------------|---------|---------------------|------|-----|
| General Properties                 | Test Method |         | Nominal Values      |      |     |
| Melt Flow Index                    | ASTM D1238  | 3.4 ~ 4 | g/10min             |      |     |
| Density                            | ASTM D792   | 0.91    | g/cm <sup>3</sup>   |      |     |
| Mechanical Properties              |             |         |                     |      |     |
| Tensile Stress (Yield)             | ASTM D638   | 93      | kgf/cm <sup>2</sup> | 9,1  | MPa |
| Elogation                          | ASTM D638   | >500    | %                   | >500 | %   |
| Flexural Modulus                   | ASTM D790   | 1100    | kgf/cm <sup>2</sup> | 107  | MPa |
| Flexural Strength                  | ASTM D790   | 48      | kgf/cm <sup>2</sup> | 4.7  | MPa |
| Notched Izod Impact Strength (23℃) | ASTM D256   | 58      | kgf∙cm/cm           | -    | J/m |
| Hardness                           | ASTM D2240  | 38      | Shore D             |      |     |
| Thermal Properties                 |             |         |                     |      |     |
| VICAT Softening Point              | ASTM D1525  | 78      | ${\mathbb C}$       |      |     |
| Additional Properties              |             |         |                     |      |     |
| Adhesion Strength                  | ASTM D903   | >3      | kgf/2cm             |      |     |

| N   | Oto. |
|-----|------|
| 1 / | OLE  |

ISO 9001, 14001, /TS 16949