

## Provisional Technical Data Sheet

### VERSALIS REVIVE® (PE) 100 LF H

LLDPE/LDPE

VERSALIS REVIVE® PE 100 LF H is a LLDPE/LDPE-based polyolefin containing 100% of post-consumer plastic from trade and industry supply chain, making it suitable for blown film technology for the production of high quality films.



Certificate n. 1915/2020

### Main Applications

VERSALIS REVIVE® PE 100 LF H is suitable for the production of films intended for various uses in secondary or tertiary packaging (e.g. shrink films, bags, hoods, silage films).

VERSALIS REVIVE® PE 100 LF H is not suitable for the production of articles and materials intended for direct contact with food, the manufacture of toys or items for early childhood and in pharmaceutical, cosmetic and / or medical applications.

### Main Properties

Resin Properties	Value	Unit	Test Method
Melt Flow Rate (190 °C/2.16 kg)	0.7	g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	-	g/10min	ISO 1133
Melt Flow Rate (190 °C/21.6 kg)	-	g/10min	ISO 1133
Density	0.930	g/cm <sup>3</sup>	ISO 1183
Melting Point	-	°C	Internal method
Moisture content	≤0.5	°C	Internal method
PP content	≤2	%	DSC method
Color	Amber	-	Visual method
Film Properties *	Value	Unit	Test Method
Tensile stress at yield MD	11	MPa	ISO 527-3
Tensile stress at yield TD	11	MPa	ISO 527-3
Tensile stress at break MD	22	MPa	ISO 527-3
Tensile stress at break TD	20	MPa	ISO 527-3
Elongation at break MD	450	%	ISO 527-3
Elongation at break TD	550	%	ISO 527-3
1% Secant modulus MD	280	MPa	ISO 527-3
1% Secant modulus TD	260	MPa	ISO 527-3
Elmendorf tear resistance MD	30	N/mm	ISO 6383-2
Elmendorf tear resistance TD	130	N/mm	ISO 6383-2
Impact resistance F50 (Dart Drop Test)	150	g	ISO 7765-1/A
Dynamic coefficient of friction (COF)	>0.5	-	ISO 8295
Haze	20	%	ISO 14782
Gloss, 45°	45	%	ASTM D 2457
Recommended film thickness	30 ÷ 120	micron	-

(\*) Typical properties of an extruded film 180 °C -210 °C, BUR 3 and 70 μm thickness. The properties of the film are to be understood as typical and may vary according to the transformation conditions and the additive package.

## Processing notes

VERSALIS REVIVE® PE 100 LF H is suitable to be transformed on blown film lines, preferably in coextrusion, into one or more internal layers and in a mixture with virgin polyethylene. The suggested melt temperature range is from 180 °C to 210 °C. The recommended thicknesses are from 30 to 120 microns. The percentages of use and the thicknesses must be evaluated according to the final characteristics of the application. If necessary, it is suggested to carry out a possible stove treatment of the granule or use suitable drying additives during the transformation.

## Storage and Handling

VERSALIS REVIVE® PE 100 LF H is supplied in pellet form and may be conveyed and bulk fed through equipment designed for conventional pelletized polyethylene resin. As with all polymeric materials, it is necessary to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping should be practiced throughout your facility. The product should be stored in dry conditions at temperatures below 50 °C and protected from sunlight. Improper storage can initiate degradation which results in odor generation, color changes and can have negative effects on the physical properties of the product. Before using this product, it is recommended to read and understand the relevant Safety Data Sheet.

## Availability

For information about availability, please refer to your Versalis representative.

## Conformity declaration

The conformity declarations and the certifications are available upon request.

---

IMPORTANT: please consult the relevant safety data sheet for more detailed information. The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information and data.

Versalis is available to provide the guaranteed values for each product on demand.