

## HOPELEX PCN-2001

Polycarbonate compound resin

### General Information

#### Description

Easy mold release  
Available in transparent, translucent and opaque color

#### Applications

Multi purpose grade (Electric & Electronic Housings, etc.)

### Typical properties<sup>1</sup>

	Test method	Typical value	Unit
<b>Physical</b>			
Melt Flow Index, 300°C, 1.2 kg	ASTM D1238	-	g/10 min
Specific Gravity	ASTM D792	1.2	
Mold Shrinkage	ASTM D955	0.5~0.7	%
<b>Mechanical</b>			
Tensile Strength, yield, 50 mm/min	ASTM D638	650	kg <sub>f</sub> /cm <sup>2</sup>
Tensile Elongation, break, 50 mm/min	ASTM D638	> 100	%
Flexural Strength, yield, 10 mm/min	ASTM D790	900	kg <sub>f</sub> /cm <sup>2</sup>
Flexural Modulus, 10 mm/min	ASTM D790	24,000	kg <sub>f</sub> /cm <sup>2</sup>
IZOD Impact Strength, notched, 23°C, 1/8"	ASTM D256	75	kg <sub>f</sub> -cm/cm
	ASTM D256	-	kg <sub>f</sub> -cm/cm
	ASTM D256	-	kg <sub>f</sub> -cm/cm
<b>Thermal</b>			
Heat Distortion Temp. 4.6 kg <sub>f</sub> /cm <sup>2</sup>	ASTM D648	-	°C
	ASTM D648	130	°C
Vicat Softening Temp. Rate B/50	ASTM D1525	-	°C
<b>Flammability</b>			
UL94 V-2	UL94	1.5	mm
UL94 V-2	UL94	3.0	mm


### Notes

ISO 9001, 14001, TS 16949

<sup>1</sup> Typical properties : these are not to be construed as specifications.

### Processing guides<sup>1</sup>

	Typical value	Unit
<b>Drying condition</b>		
Drying temperature	120	°C
Drying time	4	hr
Maximum moisture content	0.02	%
<b>Injection molding</b>		
Melt temperature	270 ~ 290	°C
Nozzle temperature	260 ~ 280	°C
Barrel	Rear zone	270 ~ 290
	Middle zone	260 ~ 280
	Front zone	250 ~ 270
Hopper temperature	60 ~ 80	°C
Mold temperature	60 ~ 90	°C



### Recycling

Sprues and runners can be reground with virgin resin within the ratio of 20%. Care must be taken to ensure that the regrind is free from impurities and regrind should not be used in applications where impact performance and/or agency compliance are required.

### Notes

ISO 9001, 14001, TS 16949

<sup>1</sup> Processing guides : Typical processing parameters are noted. Actual processing conditions will depend on machine size, mold design, material residence time, shot size, etc.