LOTTE CHEMICAL

January, 2013

KOPELEN BM-311

PP BLOCK COPOLYMER

General Information

Description 0

BM-311 is impact block copolymer which has ethylene-propylene rubber inside homo polypropylene.

This grade can be processed by sheet extrusion. B-310 shows good impact resistance at low temperature and has also high strength.

It has good vacuum molding property, suitable for the production of vacuum molding goods. BM-311 is applied to food packaging tray, various industrial sheets, conjugated duct.

0 Applications

- Vacuum forming use(food packaging tray)
- Plastic corrugated boards
- Blow molding goods
- Conjugated Duct Pipe

	Physical Properties ¹					
Physical	Test Method		Nominal Values			
Melt Flow Index	ASTM D1238	0.5	g/10min			
Density	ASTM D792	0.9	g/cm ³			
Mechanical						
Tensile Stress (Yield)	ASTM D638	260	kgf/cm ²	26	MPa	
Tensile Strain (Break)	ASTM D638	>100	%	>100	%	
Flexural Modulus	ASTM D790	11,000	kgf/cm ²	1,080	MPa	
Impact						
Notched Izod Impact Strength (23℃)	ASTM D256	50.0	kgf·cm/cm	490	J/m	
Notched Izod Impact Strength (-10 ℃)	ASTM D256	6.0	kgf·cm/cm	59	J/m	
Thermal						
Heat Deflection Temperature (4.6kgf/cm ²)	ASTM D648	100	Ĵ			
Additional Property						
Flammability	UL94	-				

NOTE

¹ Physical Properties : these are not to be construed as specifications

ISO 9001, 14001, /TS 16949

www.lottechem.com