



versalis

Provisional Data Sheet

info.styrenics@versalis.eni.com

Sinkral[®]
ABS Resin

M 4 Modena

Extrusion and co-extrusion grade with an high mattness and a very low roughness

Designation: Thermoplastic ISO 2580-ABS 1,EGN,105-08-09-15

Applications

Sinkral M 4 Modena is used in extrusion and co-extrusion of sheets and profiles that need, at the same time, high mattness and a smooth surface.

Typical processing data

Extrusion:

- if no venting, pre-drying required at 80°C for 2 - 4hr in an air circulating oven
- melt temperature 180 - 220°C

General information

This grade is available in natural color only

Properties	Test conditions	Test methods	Units	Values
General				
Density		ISO 1183	g/cm ³	1.04
Water absorption	24 h / 23°C	ASTM D 570	%	0.3
Rheological				
Melt flow rate (MFR)	220°C - 10 kg	ISO 1133	g/10 min	8
Mechanical				
Tensile strength	50 mm/min	ASTM D 638	MPa	27
Strain at break	50 mm/min	ASTM D 638	%	100
Flexural strength	2 mm/min	ASTM D 790	MPa	40
Flexural modulus	2 mm/min	ASTM D 790	MPa	1550
Izod impact strength, notched	+23°C - thickness 3.2 mm	ISO 180/4A	J/m	110
	0°C - thickness 3.2 mm	ISO 180/4A	J/m	90
	-20°C - thickness 3.2 mm	ISO 180/4A	J/m	80
	-40°C - thickness 3.2 mm	ISO 180/4A	J/m	75
	+23°C - thickness 4,0 mm	ISO 180/1A	kJ/m ²	9,5
	-40°C - thickness 4,0 mm	ISO 180/1A	kJ/m ²	7
Charpy impact strength, notched unnotched unnotched	+23°C	DIN 53453	kJ/m ²	9
	+23°C	DIN 53453	kJ/m ²	NB
	-40°C	DIN 53453	kJ/m ²	NB
Rockwell hardness	scale R	ISO 2039/2	-	R97
Thermal				
Vicat softening temperature	10 N - 120°C/h	ISO 306/A 120	°C	106
	50 N - 120°C/h	ISO 306/B 120	°C	101
Deflection temperature under load (annealed)	1.8 MPa - 120°C/h	ASTM D 648	°C	101
Coefficient of linear thermal expansion		ASTM D 696	10 ⁻⁵ /°C	9
Thermal conductivity		ASTM C 177	W/(K· m)	0.17
Moulding shrinkage		internal method	%	0.4 - 0.6
Flammability				
Flame behaviour	thickness 1.5 mm	UL 94	class	HB
Glow wire test (GWT)	thickness 3,0 mm	IEC 60695-2-1	°C	650
Electrical				
Surface resistivity	dry	IEC 60093	ohm	10E14
Volume resistivity	dry	IEC 60093	ohm·cm	10E15
Dielectric strength	dry	IEC 60243	kV/mm	30
Dielectric constant (relative permittivity)	1000 Hz - dry	IEC 60250	-	3.1
Dissipation factor	1000 Hz - dry	IEC 60250	-	15·10E-3

Revision n° 3

This Sheet is valid for six months from the revision date.

Issue 11/14

The technical information contained herein are provided for guidance purpose only. For more detailed information, please consult the relevant safety data sheet. The Company accepts no responsibility for the results obtained therefrom, as neither for their utilization in infringement of possible patent rights.

On the subject of the experimental product the Company reserves the right to change without prewarning the characteristics to optimize the performance and the cost